



HYDROPEL WB™

Breathable, Silane/Siloxane Water Repellent for Brick and Concrete Vertical Surfaces

MANUFACTURER

L&M Construction Chemicals, Inc.
14851 Calhoun Road
Omaha, NE 68152
Phone: (402)453-6600
FAX: (402)453-0244
Website: www.lmcc.com

PRODUCT DESCRIPTION

HYDROPEL WB is a water-based, VOC-compliant, non-yellowing, water repellent treatment that remains invisible while protecting surfaces from damaging water penetration. **HYDROPEL WB** quickly and easily forms a long lasting water repellent barrier within concrete and masonry. It is designed for maximum protection on above grade, vertical surfaces such as common brick and vertical concrete. **HYDROPEL WB** is compatible with most caulking compounds and sealants.

HYDROPEL WB's active ingredients provide a two-fold water repellent protection to concrete and masonry by 1) non-yellowing, surface barrier that repels water, mildew, dirt and airborne contaminants and 2) integral protection by an in-depth chemical action-forming barrier.

Basic Use: **HYDROPEL WB** is designed specifically for water repellent treatment of vertical above grade concrete and brick masonry units. Treatment is invisible and long lasting.

FEATURES & BENEFITS

- Formulated for concrete and masonry.
- Penetrates substrate for permanent hydrophobic protection.
- Odorless.
- Ready-to-use, non-flammable, non-volatile.
- Invisible, long lasting protection.
- Breathable.

ESTIMATING

This product is available in 5 gallon (18.9 liter) pails, and 55 gallon (208 liter) drums. Containers are clearly identified with product name and batch code.

Coverage Rates:

Average rate is determined by surface porosity:

	Ft ² /gallon	m ² /L
Brick.....	100-125	2.5-3.5
Dense Brick.....	175-200	4-5
Stucco.....	75-125	2-3
Precast Concrete.....	200-250	5-6
Cast In Place Concrete.....	200-250	5-6

For very porous surfaces, such as concrete block, use **HYDROBLOCK**.

TECHNICAL DATA

Applicable Standards:

ASTM-E-514
SS-W-110C
VOC Compliant

Physical Properties:

Color Milky white, dries invisible
Dry Time 70°F (20°C) Two (2) hours
Surface Gloss None
Penetration, avg. 1/16-1/4 inch
Solids, Active 6%
Resistance to Ultraviolet Rays: Excellent
Salt Spray after 1000 hrs. No surface deterioration
SS-W-110C-Water Repellency
Brick % Effective.....86%
Water Repellency, ASTM E-514,
Wind driven rain, 62 mph, 4 hours..... Excellent
VOC, gms/Liter..... <195

INSTALLATION

Surface Preparation: Areas to be treated shall be clean and dry for penetration. Allow 24 hours after rain before applying. Cure mortar joints of new masonry surfaces for 14 days prior to treatment. Clean off mud, scale, coatings or efflorescence. Repair mortar joints, other than hairline cracks, and allow to cure a minimum of 72 hours before applying **HYDROPEL WB**. Caulking and sealant work should be completed and allowed to cure before application.

Apply **HYDROPEL WB** with low pressure airless spray equipment. A garden sprayer is acceptable for small projects. Spray pressure should be no more than 20 psi. Control over-spray. **HYDROPEL WB** bonds to all silicious materials including glass.

Not recommended for highly permeable surfaces. Some substrates may require several flood coats. Treat vertical areas using horizontal passes. Saturate mortar joints. Application from the bottom up is necessary to provide uniform penetration. Use an overlapping pattern allowing materials to flood down from contact point approximately 8 inches (200mm). Apply a light mist coat before general application to help insure complete saturation.

Clean up: Clean up equipment and overspray immediately with soap and water. For dried residue, scrub with very hot water and mild citric acid.

NOTE: **HYDROPEL WB** requires approximately seven (7) days after application to develop its maximum water repellency. After this initial curing period,



HYDROPEL WB



surfaces remain permanently treated to resist water penetration. Fully cured surfaces also resist further treatment.

FOR BEST RESULTS:

Use **HYDROPEL WB** on masonry and concrete surfaces only. Highly permeable units require several flood coats. Not to be used for limestone, marble or other non-siliceous stone surfaces. Not to be used on concrete block or very porous surfaces. Not to be used for below grade applications. Keep off shrubbery and plant life. Do not apply in temperatures below 45°F (6°C). Do not apply in high winds. Do not dilute.

HYDROPEL WB will not inhibit water penetration through unsound or cracked surfaces or surfaces with detective flashing, caulking, or structural waterproofing.

PRECAUTIONS

Keep from freezing. **HYDROPEL WB** can be made useless by freezing. Keep in a closed container when not in use. Avoid prolonged skin contact. Wash hands with soap and water. Wear protective gloves and goggles. Do not inhale mist. Do not return unused materials to container.

Please refer to Product Material Safety Data Sheet (MSDS) before using.

STORAGE/SHELF LIFE

HYDROPEL WB containers are to be sealed and stored in a clean, dry area between 45-85°F (6-29°C). Keep from freezing. Shelf life is one year in unopened containers.

FAX ON DEMAND/WEBSITE

Instant access, 24 hours a day --- 7 days a week to concrete information can be found in two convenient forms, Fax On Demand and L&M's internet website. L&M's exclusive Fax On Demand and its convenient internet website offer instant access to Technical Data Sheets, Material Safety Data Sheets, product updates, and other useful information. Simply dial 800-839-9887 or visit www.lmcc.com and follow the easy steps. L&M is ready to respond to your concrete information needs - anytime anywhere!

SHORT SPEC

07180: Water repellent treatment: For vertical concrete and masonry surfaces. VOC compliant silane/siloxane blend, minimum 6% active ingredients, odorless, invisible. "**HYDROPEL WB**" by L&M Construction Chemicals, Inc.

LIMITED WARRANTY

Contact L&M for information on available five year performance warranty, which requires the use of an approved L&M installer.

This product is warranted to be free of defects in material and workmanship, and conform to L&M Construction Chemicals ("L&M") quality control standards. All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty or guaranty of any kind, expressed or implied including but not limited to, an implied warranty of merchantability or an implied warranty of fitness for a particular purpose. Satisfactory results depend upon many factors beyond L&M's control. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk, loss, damage, expense and liability resulting from his or her direct use, indirect use or consequential to their use of the product. L&M shall not be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use or inability to use the product. L&M's sole responsibility shall be to replace that portion of the product which proves to be defective. Any warranty claim must be made within six (6) months from the date of the claimed breach. This limited warranty applies only if the product was properly installed and used according to all instructions and was properly stored prior to use.

For Professional Use Only.

©2005, L&M Construction Chemicals, Inc